

Product Data Sheet



Product

Silver – Silver Chloride Inks

| Product | Ag/AgCl Ratio | Conductivity (ohm/sq/mil) | Parts | Commonly Used Cure Temps (°C) | Comments |
|-----------|---------------|---------------------------|-------|-------------------------------|---|
| 22-106-12 | 55:45 | 25 | 1 | 100 – 130 | Silver/Carbon/Silver Chloride, screen-printable |
| 22-113-09 | 82:18 | 0.05 | 1 | 100 – 160 | Extremely flexible, screen-printable |
| 22-115-02 | 80:20 | 0.10 | 1 | 100 – 120 | Flexographic printable |
| 22-117-23 | 70:30 | 0.05 | 1 | 100 – 160 | Extremely flexible, screen-printable |
| 22-117-43 | 85:15 | 0.08 | 1 | 100 – 150 | Waterbased, screen-printable |
| 22-119-10 | 95:5 | 0.05 | 1 | 100 – 175 | Pad-printable |
| 22-124-36 | 66:34 | 0.05 | 1 | 100-160 | Extremely flexible, screen-printable |
| 22-125-20 | 95:5 | 0.02 | 1 | 125 -175 | Chemically resistant, epoxy based, screen-printable |
| 22-125-21 | 65:35 | 0.02 | 1 | 125 – 175 | Chemically resistant, epoxy based, screen-printable |

The information contained herein, is, to the best of our knowledge accurate. However, MicroCoat Technology does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchasers in selecting the appropriate products for purchaser's own testing. All products may present unknown hazards and should be used with the proper precautions. Although certain hazards are described herein and in the Material Safety Data Sheets, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.