



Product Data Sheet

Product

MicroCoat 3638-HT

A Single Component, Toughened, Microelectronic Grade non-Conductive Die Attach Adhesive with a Service Temperature of <-65°C to Over >340°C, a Thermal Conductivity of 4W/mK and Meets NASA Low Outgassing Specifications

MicroCoat 3638-HT is an Aluminum nitride filled die attach adhesive that features a unique blend of high performance properties including both high shear and peel strengths along with convenient handling and high/low temp properties. This is a one component system formulated to cure at elevated temperatures.

3638-HT has a number of outstanding processing advantages;

- No mixing is necessary prior to use
- This material is **not** "Pre-mixed and Frozen"
- The viscosity remains constant with time (i.e. it will not thicken over time)
- Working life is unlimited at room temperature, and the material is room temperature storable
- No cleanup required in-between shifts

MicroCoat 3638-HT forms high strength bonds for service over the remarkably wide temperature range of <-65°C to over 300°C and is used for die attach on virtually any substrate material. As a toughened system, 3638-HT offers superior resistance to impact, thermal shock, vibration and stress fatigue cracking. It is 100% reactive and does not contain any diluents or solvents and may be used in "down-the-hole" environments at >2K meters.

3638-HT is remarkably resistant to severe thermal cycling and many chemicals including water, oil, fuels and most organic solvents even upon prolonged exposures. Adhesion to metals, glass, and ceramics is excellent. The cured epoxy is a superior electrical insulator and is colored tan (*this material will darken when exposed to high temperature with NO adverse effects on the adhesive*). MicroCoat Polymer System 3638-HT high performance coupled with its convenient handling make it widely used in a variety of applications in the aerospace, electronic, microelectronics, electrical, automotive and chemical industries. MicroCoat 3638-HT will meet NASA low outgassing specifications.

Product Advantages

- A single component system; no mixing required prior to use, no viscosity changes over time.
- **Room temperature storable; not premixed and frozen!**
- Versatile cure schedules.
- High shear and peel strength to similar and dissimilar substrates over the remarkably wide temperature range of -65°C – 340°C. (Note: Color changes to slightly amber >300°C)
- Good electrical insulating properties and chemical resistance.
- True thermal conductivity of 3.978W/mK
- Superior thermal shock, impact and stress cracking fatigue resistance,
- Will meet NASA low outgassing per ASTM E-595, NASA MSFC 1443, Mil-Std-883 5011.4 (3.8.6)
- RoHS Compliant

MicroCoat Technologies

MicroCoat 3638-HT

Product Properties

| | |
|--|-----------------------------------|
| Solids content, % | 100 |
| Specific Gravity | 1.6 |
| Viscosity @ 25°C, Kcps | 15-20 |
| Filler | Aluminum Nitride |
| Filler Particle Size | Avg 7-8 um Max 12um |
| Color | Yellow |
| Tensile shear on Silicon Die @ 25C psi.....(Shears Die) | >3,200 |
| Tensile strength, 25°C, psi | >8,500 |
| Flexural strength, 25°C, psi | >9,700 |
| Compressive strength, 25°C, psi | >30,000 |
| Elongation | 3.8% |
| Shore hardness (Shore D) | 80 |
| Tensile modulus, 25°C, psi | 350,000 |
| Die Shear 5mm X 5mm psi | Die Break 100% |
| Maximum total mass loss (TML) | <1.0% of the original sample mass |
| Maximum collected volatile condensable material (CVCM) deposition | <0.1% |
| Tg: | >130°C |
| CTE | 130 ppm per °C |
| CTE below the Tg | 50-55 ppm |
| CTE above Tg | >100 ppm |
| Youngs Modulus; | 450-500K |
| Thermal Conductivity | 3.978 W/mK |
| Service temperature range | -100C to 340°C |
| Short Term High Temp | 375°C |
| Post Cure Ionics 883/5011.3.8.7 | Cl=<5ppm, Na+<=3.3ppm, K+<=1.1ppm |
| Teflon Flask 5 gm sample using 20-40 mesh, 50 gm DI H ₂ O, 100°C for 24 hours | |

Cure Schedule Mechanical Convection Oven or Conveyor; 30 minutes @ 125°C followed by 60 minutes @ 150°C

Shelf life/Pot Life at 25°C; 6 months. 12 months Refrigerated. Do not freeze. Usually depends on ambient conditions.

· Available in 3cc, 10cc, and 30cc syringes only.

EXTENDED SHELF LIFE UP TO 12 MONTHS IF KEPT REFRIGERATED *NOT FROZEN!!*

The information contained herein, is, to the best of our knowledge accurate. However, MicroCoat Technology does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchasers in selecting the appropriate products for purchaser's own testing. All products may present unknown hazards and should be used with the proper precautions. Although certain hazards are described herein and in the Material Safety Data Sheets, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.